

# AWTA PRODUCT TESTING

Australian Wool Testing Authority Ltd - trading as AWTA Product Testing  
A.B.N 43 006 014 106

1st Floor, 191 Racecourse Road, Flemington, Victoria 3031  
P.O Box 240, North Melbourne, Victoria 3051  
Phone (03) 9371 2400 Fax (03) 9371 2499

## TEST REPORT

**Client :** Gerflor Australasia Pty Ltd  
17 Cato Street  
Hawthorn East VIC 3123

**Test Number :** 15-002344  
**Issue Date :** 03/06/2015  
**Print Date :** 3/06/2015

**Sample Description** Clients Ref : "Texline Comfort"  
Vinyl flooring with textile backing  
Nominal Composition : Polyurethane finish, clear PVC wear layer, patterned foam, fibreglass interlayer, anti-mildew bonding layer, compact foam balancing layer and fibre backing  
Nominal Mass per Unit Area/Density : 2440g/m<sup>2</sup>  
Nominal Thickness : Approx: 5mm

### AS/ISO 9239.1-2003

#### Reaction to Fire Tests for Floorings. Determination of the Burning Behaviour using a Radiant Heat Source

Date of Sample Arrival 21/05/2015  
Date Tested 03/06/2015

CHF Value	1	2	3	Mean
Length	4.6	5.5	5.3	5.1 kW/m <sup>2</sup>
Width	6.1	-	-	- kW/m <sup>2</sup>
Smoke Value	1	2	3	Mean
Length	137	167	150	151 %.min
Width	202	-	-	- %.min

Blistering Yes

The test results relate to the behaviour of the test specimens of a product under the particular conditions of the test, they are not intended to be sole criterion for assessing the potential fire hazard of the product in use.

Sample was conditioned in accordance with BSEN 13238:2001 at a temperature of 23±2°C and relative humidity of 50±5% for a minimum of 48 hours prior to testing.

Each specimen was clamped to a substrate of 6mm thick fibre reinforced cement board prior to testing.

25889

5015

Page 1 of 1

